



BY **SKUBA**[®]

ESSENCE

VINYL FLOOR . SPC



SUITABLE FOR
BATHROOM




WEAR RESISTANT
& STAIN RESISTANT



SUITABLE FOR
KITCHENS



CASTOR CHAIR
RESISTANT




NATURAL
LOOK & FEEL



SUITABLE FOR
FLOOR HEATING



MOISTURE
RESISTANT



EASY
CLEAN

UNICLIC 

SAND

Nobre



RODAPÉ REF

REF **BRANCO** 1926

PERFIL REF

REF **1506**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



BY SKUBA®



PEARL

Elegante



RODAPÉ REF

REF **1905**

REF **BRANCO** 1926

PERFIL REF

REF **1952**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



URBAN

Moderno



RODAPÉ REF

REF **1915**

REF **BRANCO** 1926

PERFIL REF

REF **1841.1852**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



44 GOLD

Luxuoso



RODAPÉ REF

REF **1506**

REF **BRANCO** 1926

PERFIL REF

REF **1506**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



SILVER

Relaxante



RODAPÉ REF

REF **1 8 4 1**

REF **BRANCO** 1926

PERFIL REF

REF **1841.1852**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



ICE

Suave



RODAPÉ REF

REF **BRANCO** 1926

PERFIL REF

REF **8 4 6 1**

REF **ALUMÍNIO**

DIM 1220 x 182 x 5,5 MM (0,3 MM)

UNICLIC 

ESSENCE
VINYL FLOOR . SPC



ESSENCE

VINYL FLOOR . SPC

ESPECIFICAÇÃO DO PRODUTO

Product Specification

Comprimento Length		1220mm 48.03 in
Largura Width		182 mm 7.16 in
Espessura Total Total Thickness	EN 428	5,5 mm 217 mils
Camada de Desgaste Wear Layer	EN 429	0,30 mm 12 mils
Peso Total Total Weight	EN 430	8,35 kg/m ² 18,41 lb/m ²
Caixa Box	10 Peças 10 Boards	2,22m ² 23,895 ft ²
Palete Pallet	55 Caixas 55 Boxes	122,1m ² 1314,27 ft ²
Peso Palete Weight Pallet	Kg/ Paleta Lb/ Pallet	1037,55 Kg 2287,41 Lb
Tratamento Superfície Surface Treatment		PUR
Classe de Uso Use Class	EN 685	23 - 31

PT | + Acessórios disponíveis. EN | + Accessories available.



DADOS TÉCNICOS | TECHNICAL DATA

RESULTADO DOS TESTES

Test Results

Estabilidade da Dimensão Dimension stability	ASTM F2199-09 (R2014)	Manf. direction: -0.046% Across-manf. direction: -0.009%
Determinação da estabilidade dimensional Determination of dimensional stability	ISO 23999:2012	MD:-0.05% AMD: 0% 0mm
Ondulação Curling	ISO 23999:2008	Average: 0.5mm pass
Solidez da cor Colour Fastness	EN ISO 105-B02:2014	Grade 6
Classe de Fogo Fire Class	EN 9239-1 EN ISO11925 - 2 EN 13501 - 1	Bfl - S1
Anti-derrapante Slip resistance	EN13893	Class DS R10
Propensão à eletricidade estática Static Electrical Propensity	EN 1815:2016 method A	0.2kV
Resistência do Encaixe Locking strength	ISO 10582:2017 Annex D	Long side(X): 7.6 kN/m Short side(Y): 6.3 kN/m Pass
Força de Ligação Seam Strenght	EN 684:1995	Ave: 360N/50mm Amd: 330N/50mm
Resistência Camada Desgaste Resilient floor covering Determination of peel resistance	EN ISO 24345:2012	Longitudinal direction: 95N/50mm Cross direction: 95N/50mm
Resistência Química Chemical Resistance	ASTM F1700 - 13a ASTM F925 - 13	no change OK
Resistência ao Impacto Impact Resistance	ANSI LF - 01 - 2011	no cracks 2500 mm
Resistência às Rodas das Cadeiras Castor chair(25000 Cycles)	NALFA/ANSI LF-01-2011 ISO4918:2016 EN 425:2002	No damage was found after test
Resistência a manchas Resistance to staining	ISO 26987:2008	Index 0: Not affected Pass
Resistência a bactérias Resistance to bacteria	ISO 846-1997 Method C	Assessment of bacteria growth: 0 pass



BY SKUBA®

VINYL FLOOR . SPC

ESSENCE

BY SKUBA